



## Product Data sheet

## Alkymok 131 W 70

Delivery form  
60% in W.S , 70% in W.S

Long – oil, air – drying alkyd resin based on soya fatty acid

### Application

- Shining constructional paints
- Decorative paints
- Polish

Solids content	70% $\pm$ 2
Viscosity 50%	90 -140 sec
Acid value	Max 10
Density, g/m <sup>3</sup>	0.91 $\pm$ 0.01
Color	Max 5
Oil Length	62%

### Principal properties

- Good weathering & yellowing resistance
- Good brush ability
- Gloss

### Solubility

White spirit	Complete
Xylene	Complete
Butyl acetate	Complete
MEK	Complete
N-butanol	Limited

### Storage and transportation

To be stored and transported at a temperature below 35 C/95F . Packaging not to be exposed to direct heat radiation.