

**Product Data sheet****Alkymok 115 BR W 70****Delivery form****60% in W.S , 70% in W.S****Long – oil, air – drying alkyd resin based on soya fatty acid****Application**

- Shining constructional paints
- Decorative paints
- Polish

Solids content	70 ± 2
Viscosity 42%	25 - 35 sec
Acid value	Max 10
Color	Max 4
Oil Length	60%
Density, g/m3	0.91 ±0.01

Principal properties

- Good weathering & yellowing resistance
- Good brush ability
- Gloss

Solubility

White spirit	Complete
Xylene	Complete Butyl
acetate	Complete
MEK	Complete
N-butanol	Limited

Storage and transportation

To be stored and transported at a temperature below 35 C/95F . Packaging not to be exposed to direct heat radiation.