

**Product Data sheet****Alkymok 115 W-70**

Delivery form

60% in W.S , 70% in W.S

Long – oil, air – drying alkyd resin based on soya fatty acid**Application**

- Shining constructional paints
- Decorative paints
- Polish

Solids content	70 ± 2
Viscosity 42%	50 -70 sec
Acid value	Max 10
Color	Max 4
Oil Length	60%
Density,g/cm3	0.92±0.01

Principal properties

- Good weathering & yellowing resistance
- Good brush ability
- Gloss

Solubility

White spirit: Complete

Xylene : Complete

Butyl acetate : Complete

MEK : Complete

N-butanol : Limited

Storage and transportation

To be stored and transported at a temperature below 35 C/95F . Packaging not to be exposed to direct heat radiation.